





# EPOXY 4500 UV RESISTANT

**DATA SHEET**

REVISION DATE FEB 2018

## CONCRETE PREPARATION

Before coating is applied, concrete must be:

- Dry – No wet areas
- Clean – Contaminants removed
- Profiled – Direct to concrete surface must be diamond ground, over epoxy surface must be sanded.
- Sound – All cracks and spalled areas repaired

Note: Mechanical preparation is the preferred method of preparing concrete for coating application. Shot-blasting, diamond grinding, scarifying and scabbling are all acceptable methods.

## PATCHING

Voids, cracks and imperfections will be seen in finished coating if the concrete is not patched correctly. Patch concrete with E2U Patch. After the patching material is cured, diamond grind patch. If another patching material is used, contact a E2U technical representative for a compatible and approved alternative.

## MOISTURE VAPOR EMISSIONS WARNING

All concrete floors without effective moisture vapor barrier are subject to possible moisture vapor transmission that may cause blistering and failure of the coating system. It is the applicator's responsibility to conduct calcium chloride and relative humidity probe testing to determine vapor emissions prior to applying any coating. Epoxy2U can supply moisture remediation products, MVB15 (MOISTURE VAPOR BARRIER).

EPOXY2U, sales agents will not be responsible for coating failures due to undetected moisture vapor emissions.

## MIXING

The ratio of Epoxy 45 is 2 to 1. That is, two parts A (resin) to one part B (hardener). Mix the following with a drill and mixing paddle. Note: If using a drill mixer, use a low speed (not to exceed 300 rpm) to prevent air entrapment.

E2U Epoxy is designed to be immediately poured on the floor. Leaving mixed product in the container will greatly reduce pot life. Once poured out on the floor, 45-60 minutes of working time can generally be expected.

## CLEAN UP

While in an un-reacted state, may be cleaned up with hot water and degreaser. Isopropyl alcohol or acetone may be needed once the resin begins hardening. Lastly, a strong solvent like Acetone may be required if resin is nearly set up.

### WARNING! SLIP AND FALL PRECAUTIONS

OSHA and the American Disabilities Act (ADA) have now set enforceable standards for slipresistance on pedestrian surfaces. The current coefficient of friction required by ADA is .6 on level surfaces and .8 on ramps. E2U Flooring recommends the use of angular slipresistant aggregate in all coatings or flooring systems that may be exposed to wet, oily or greasy conditions.

It is the contractor and end users' responsibility to provide a flooring system that meets current safety standards. E2U or its sales agents will not be responsible for injury incurred in a slip and fall accident.

**KEEP OUT OF REACH OF CHILDREN**

## APPLICATION INSTRUCTIONS

Application of E2U Epoxy 4500 for a nominal 20 to 30 mil coating system is applied in a single coat.

1. Always apply in descending temperatures. Concrete is porous and traps air. In ascending temperatures (generally mornings) the air expands and can cause out gassing in the coating. It is safer to apply coatings in the late afternoon, especially for exterior applications.
2. Optimum ambient temperature should be between 55-90°F during application. Note: Cure times are affected by ambient and slab temperatures. Temperatures of 55°F and lower can slow cure times. Temperatures of 85°F and higher will shorten working times.
3. Apply at approximately to desired spread rate of 50-200 SF/gal by immediately pouring out blended material in a wavy ribbon while walking and pouring at the same time until Bucket is empty.
4. Using a squeegee on a pole, pull E2U Epoxy 4500 at a uniform thickness over areas to be coated.
5. Using a 3/8" non-shedding phenolic (plastic) core paint roller, roll coating for-wards and backwards.
- 6 Lastly, back roll in the opposite direction as step 5

### Handling Precautions

Use only with adequate ventilation. Appropriate cartridge-type respirator must be used during application in confined areas. Avoid contact with skin. Some individuals may be allergic to epoxy resin. Protective gloves and clothing are recommended.

### WARRANTY

E2U products are warranted for one year after date of purchase. Please refer to the Limited Material warranty for additional clarification.



**MADE IN THE USA**

## TECHNICAL DATA SHEET

4602 S 36th St • Phoenix AZ 85040 • 855.EPOXY2U (376.9928) • www.Epoxy2U.com

Revised Sep 2019